

## **TECHNICAL DATA \$HEET**

IPRODUCT NAME:	Crono D	
PRODUCT CODE:	Crepe Paper SVCP	
PRODUCT CODE: PRODUCT SIZES		
PRODUCT SIZES	Crepe Paper 300 mmx300mm	SVCP3030 SVCP4040
	Crepe Paper 400 mm x400 mm	SVCP4040 SVCP5050
	Crepe Paper 500 mm x500 mm	
	Crepe Paper 600 mm x600 mm	SVCP6060
	Crepe Paper 750 mm x750 mm	SVCP7575
	Crepe Paper 900 mm x900 mm	SVCP9090
	Crepe Paper 1000 mm x1000 mm	SVCP100100
	Crepe Paper 1200 mm x1200 mm	SVCP120120
	Crepe Paper 1500 mm x1500 mm	SVCP150150
RELATED STANDARDS:	Medical Device Reg	
	SV Sterilization Crepe Paper is a ty is used to wrap and protect medica during the sterilization process. It is temperatures and pressure during compromising the sterility of the com	Il equipment and supplies designed to withstand high sterilization without tearing or
OPERATION CONDITIONS:	The crepe paper is covered with au be securely closed after being rolled commonly used in hospitals, clinics, maintain the cleanliness and sterilit supplies. <b>PRODUCT SPECIFICATIONS</b>	up. Sterilization crepe paper is and other healthcare settings to
	CREPE PAPER	
PROPERTY	UNIT	<b>TYPICAL VALUE</b>
SUBSTANCE	g/m²	60,3
THICKNESS	micron	
TENSILE STRENGHT MD	N/15mm	141,00
	11,131111	141,00 21,3
TENSILE STRENGHT CD	N/15mm	
TENSILE STRENGHT CD WET STRENGHT MD		21,3
	N/15mm	21,3 17,1
WET STRENGHT MD	N/15mm N/15mm	21,3 17,1 6,8
WET STRENGHT MD WET STRENGHT CD	N/15mm N/15mm N/15mm	21,3 17,1 6,8 5,2
WET STRENGHT MD WET STRENGHT CD BREAKING LENGTH MD	N/15mm N/15mm N/15mm km	21,3 17,1 6,8 5,2 2,4
WET STRENGHT MD WET STRENGHT CD BREAKING LENGTH MD BREAKING LENGTH CD	N/15mm N/15mm N/15mm km km	21,3 17,1 6,8 5,2 2,4 1,8
WET STRENGHT MD WET STRENGHT CD BREAKING LENGTH MD BREAKING LENGTH CD STRETCH MD	N/15mm N/15mm N/15mm km km %	21,3 17,1 6,8 5,2 2,4 1,8 9,2
WET STRENGHT MD WET STRENGHT CD BREAKING LENGTH MD BREAKING LENGTH CD STRETCH MD BURST STRENGHT	N/15mm N/15mm N/15mm km km % kPa kPa ml/min	21,3 17,1 6,8 5,2 2,4 1,8 9,2 117
WET STRENGHT MD WET STRENGHT CD BREAKING LENGTH MD BREAKING LENGTH CD STRETCH MD BURST STRENGHT AIR PERMEABILITY	N/15mm N/15mm N/15mm km km % kPa	21,3 17,1 6,8 5,2 2,4 1,8 9,2 117 4581
WET STRENGHT MD WET STRENGHT CD BREAKING LENGTH MD BREAKING LENGTH CD STRETCH MD BURST STRENGHT AIR PERMEABILITY WATER ABSORBENCY	N/15mm N/15mm N/15mm km km % kPa kPa ml/min	21,3 17,1 6,8 5,2 2,4 1,8 9,2 117 4581 23

MANIFACTURER	BF MEDİKAL SANAYİ İTHALAT İHRACAT TİCARET LTD.ŞTİ. Feridun Çelik Mah. 1743. Sok. No:6/B Altındağ Ankara/TURKEY 06360 Mail: export@sterivision.com.tr // Web: www.sterivision.com.tr
	Mail: export@sterioision.com.tr // web: www.sterioision.com.tr